

ROMACON[®] PETRO

PIPELINE REPAIR PRODUCTS FOR HIGH PRESSURE PIPES IN THE OIL- GAS- AND PETROCHEMICAL INDUSTRY

ANSI TABLE

Working pressure by classes, psig							
class Temp. F	150	300	400	600	900	1500	2500
-20 to 100	285	740	990	1480	2220	3705	6170
200	260	675	900	1350	2025	3375	5625
300	230	655	875	1315	1970	3280	5470
400	200	635	845	1270	1900	3170	5280
500	270	600	800	1200	1795	2995	4990
600	140	550	730	1095	1640	2735	4560
650	125	535	715	1075	1610	2685	4475
700	110	535	710	1065	1600	2665	4440
750	95	505	670	1010	1510	2520	4200
800	80	410	550	825	1235	2060	3430
850	65	270	355	535	805	1340	2230
900	50	170	230	345	515	860	1430
950	35	105	140	205	310	515	860
1000	20	50	70	105	155	260	430

Test pressure = 1.5 x (working pressure based on class and temperature)
Environment conditions -20 to 100 degrees F.

Offices and factory:
Kerkdijk-Zuid 11a
5492 HW Sint Oedenrode
The Netherlands

T +31 88 765 44 50
F +31 88 765 44 51

E sales@romaconpetro.com

